


2200 B Zanker Rd, San Jose, CA 95131 Phone: +1 408 432 1000 Fax: +1 408 228 3924 www.mir-mosaic.com E-mail: info@mir-mosaic.com

## **NETHERLANDS COLLECTION**

Product Name:
Product Code:
Material:
Surface:
Sheet Size:
Thickness:
Sheet Coverage Area:
Chip Size:
Quantity in a box:
Sq.ft/box:
Lead Time:

MONDRIAN VELVET JP-302 glass 11.3x11.3" 5/16" 0.89 sq.ft 1.2x1.2\*5/16" 5 sheets/ctn 4.43 sq.ft Stocked





Water absorption - 0.1% Chemical resistance – resistant Bond Strength 28-day dry – 225psi Bond Strength 21-day dry + 7 day submerged - 91psi