

CHARACTERISTICS PORCELAIN (Group Bla)

DATE: 07/11/2017

MODEL: ACADIA BLANCO / GRIS SIZE 15X90	SERIE ACADIA CODE 200000000000013243
---	---

1.-CLASSIFICATION (UNE-EN 14411).
Dry Pressed Ceramics Tiles with low water absorption - Group Bla, E ≤ 0,5% for internal and external floors and walls.

2.-SPECIFICATIONS (UNE-EN 14.411 - ISO13.006)

REQUIREMENTS	STANDARD APPLIED	REQUIREMENTS STANDARD	TEST RESULTS
Dimensions and Surface Quality	ISO 10545-2	---	PASS
Water Absorption	ISO 10545-3	E ≤ 0,5 %	PASS
Modulus of Rupture	ISO 10545-4	≥ 35 N/mm ²	PASS
MOHS	EN 101	(*)	6
Crazing Resistance	ISO 10545-11	(*)	PASS
Resistance to chemicals			
- Household chemicals: Ammonium chloride solution 100 g/l	ISO 10545-13	Min B	GA
- Swimming pool salts: Sodium Hypochlorite solution 20 mg/l		Min B	GA
- Acids and alkalis:			
Low concentrations: Hydrochloric acid solution (3%)		(*)	GLA
Citric acid solution 100 g/l		(*)	GLA
Potassium hydroxide 30 g/l		(*)	GLA
High concentrations: Hydrochloric acid solution (18%)		(*)	GHA
Lactic acid solution (5%)		(*)	GHA
Potassium hydroxide 100 g/l		(*)	GHA
Resistance to staining: Cr2O3/FE2O3 + light oil		ISO 10545-14	Min 3
Abrasion Resistance (PEI):	ISO 10545-7	(*)	IV
Frost Resistance	ISO 10545-12	Required	PASS
Slip resistance	DIN 51130 (R) ANSI 137.1 (DCOF) UNE-ENV 12633(Clas)	(*) (*) (*)	R9 >0,42 27º/1

3.-APPLICATION GROUPS
According to its characteristics, Hijos de F. Gaya Fores, defines this model as group:

GRUPO D

(*) as manufacturer confirms

CHARACTERISTICS PORCELAIN (Group Bla)

DATE: 07/11/2017

MODEL: ACADIA SPIGA BLANCO / GRIS SIZE 45X90	SERIE ACADIA CODE 200000000000013246
---	---

1.-CLASSIFICATION (UNE-EN 14411).
Dry Pressed Ceramics Tiles with low water absorption - Group Bla, E ≤ 0,5% for internal and external floors and walls.

2.-SPECIFICATIONS (UNE-EN 14.411 - ISO13.006)

REQUIREMENTS	STANDARD APPLIED	REQUIREMENTS STANDARD	TEST RESULTS
Dimensions and Surface Quality	ISO 10545-2	---	PASS
Water Absorption	ISO 10545-3	E ≤ 0,5 %	PASS
Modulus of Rupture	ISO 10545-4	≥ 35 N/mm ²	PASS
MOHS	EN 101	(*)	6
Crazing Resistance	ISO 10545-11	(*)	PASS
Resistance to chemicals			
- Household chemicals: Ammonium chloride solution 100 g/l	ISO 10545-13	Min B	GA
- Swimming pool salts: Sodium Hypochlorite solution 20 mg/l		Min B	GA
- Acids and alkalis:			
Low concentrations: Hydrochloric acid solution (3%)		(*)	GLA
Citric acid solution 100 g/l		(*)	GLA
Potassium hydroxide 30 g/l		(*)	GLA
High concentrations: Hydrochloric acid solution (18%)		(*)	GHA
Lactic acid solution (5%)		(*)	GHA
Potassium hydroxide 100 g/l		(*)	GHA
Resistance to staining: Cr2O3/FE2O3 + light oil		ISO 10545-14	Min 3
Abrasion Resistance (PEI):	ISO 10545-7	(*)	IV
Frost Resistance	ISO 10545-12	Required	PASS
Slip resistance	DIN 51130 (R) ANSI 137.1 (DCOF) UNE-ENV 12633(Clas)	(*) (*) (*)	R9 >0,42 27º/1

3.-APPLICATION GROUPS
According to its characteristics, Hijos de F. Gaya Fores, defines this model as group:

GRUPO D

(*) as manufacturer confirms

1.- CLASSIFICATION.

Water abs. production	Group I E ≤ 3 %	Group IIa 3 % < E ≤ 6 %	Group IIb 6 % < E ≤ 10 %	Group III E > 10 %
A Extruded	Group AI ISO 13006 Annex A1	Group AIIa ISO 13006 Annex A2a	Group AIIb ISO 13006 Annex A2b	Group AIII ISO 13006 Annex A3
B Dry pressed	Group BIa E ≤ 0,5 % ISO 13006 Annex BIa	Group BIla ISO 13006 Annex B2a	Group BIlb ISO 13006 Annex B2b	Group BIII ISO 13006 Annex B3
C Others	Group CI	Group CIIa	Group CIIb	Group CIII

1.- CLASSIFICATION.

Water abs. production	Group I E ≤ 3 %	Group IIa 3 % < E ≤ 6 %	Group IIb 6 % < E ≤ 10 %	Group III E > 10 %
A Extruded	Group AI ISO 13006 Annex A1	Group AIIa ISO 13006 Annex A2a	Group AIIb ISO 13006 Annex A2b	Group AIII ISO 13006 Annex A3
B Dry pressed	Group BIa E ≤ 0,5 % ISO 13006 Annex BIa	Group BIla ISO 13006 Annex B2a	Group BIlb ISO 13006 Annex B2b	Group BIII ISO 13006 Annex B3
C Others	Group CI	Group CIIa	Group CIIb	Group CIII

2.-CHARACTERISTICS

RESISTANCE TO	CLASS	MEANING
Stains	5	The stain is removed with hot water and a damp cloth
	4	The stain is removed with a weak cleaning agent.
	3	The stain is removed with mechanical cleaning and a strong cleaning agent.
	2	The stain is removed with suitable solvent after immersion for 24 h.
	1	The stain is not removed
Household chemicals Swimming pool salts	GA(V)	Non Visible effect (if the hue becomes slightly different, this is Definite change in appearance
	GB(V)	Definite change in appearance
	GC(V)	Partial or complete loss of the original surface
Acids and alkalis	GLA(V)	Non Visible effect (if the hue becomes slightly different, this is Definite change in appearance
	GLB(V)	Definite change in appearance
	GLC(V)	Partial or complete loss of the original surface
Low concentrations (L)	GHA(V)	Non Visible effect (if the hue becomes slightly different, this is Definite change in appearance
	GHB(V)	Definite change in appearance
	GHC(V)	Partial or complete loss of the original surface

2.-CHARACTERISTICS

RESISTANCE TO	CLASS	MEANING
Stains	5	The stain is removed with hot water and a damp cloth
	4	The stain is removed with a weak cleaning agent.
	3	The stain is removed with mechanical cleaning and a strong cleaning agent.
	2	The stain is removed with suitable solvent after immersion for 24 h.
	1	The stain is not removed
Household chemicals Swimming pool salts	GA(V)	Non Visible effect (if the hue becomes slightly different, this is Definite change in appearance
	GB(V)	Definite change in appearance
	GC(V)	Partial or complete loss of the original surface
Acids and alkalis	GLA(V)	Non Visible effect (if the hue becomes slightly different, this is Definite change in appearance
	GLB(V)	Definite change in appearance
	GLC(V)	Partial or complete loss of the original surface
Low concentrations (L)	GHA(V)	Non Visible effect (if the hue becomes slightly different, this is Definite change in appearance
	GHB(V)	Definite change in appearance
	GHC(V)	Partial or complete loss of the original surface

3.- APPLICATIONS GROUPS

GROUP A.- Recommended for moderate or low level transit. Suitable for bedrooms and/or bathrooms in houses (avoid any kind of abrasion).

GROUP B.- Suitable for light or medium transit, such as rooms inside houses, except for kitchens or areas with direct access from outside.

GROUP C.- Floorings recommended for medium transit, suitable for houses, allkind of rooms included kitchen or near to entrance area.

GROUP D.- Flooring suitable for heavy traffic, such as entrances to houses with direct access from the outside, all kind of rooms and professional offices.

GROUP GRAN TRANSITO.- Flooring suitable and recommended for very heavy traffic

3.- APPLICATIONS GROUPS

GROUP A.- Recommended for moderate or low level transit. Suitable for bedrooms and/or bathrooms in houses (avoid any kind of abrasion).

GROUP B.- Suitable for light or medium transit, such as rooms inside houses, except for kitchens or areas with direct access from outside.

GROUP C.- Floorings recommended for medium transit, suitable for houses, allkind of rooms included kitchen or near to entrance area.

GROUP D.- Flooring suitable for heavy traffic, such as entrances to houses with direct access from the outside, all kind of rooms and professional offices.

GROUP GRAN TRANSITO.- Flooring suitable and recommended for very heavy traffic



Designs for your lifestyle



Exclusive Distributors:
 MIR Group, Inc.
 2200 B Zanker Rd, San Jose, CA 95131
 Ph: +1 408 432-5400,
 +1 408 432-1000
 fax: +1 408 228-3924
 e-mail: info@mir-mosaic.com
www.facebook.com/mir.mosaic
www.mir-mosaic.com

ACADIA

ACADIA




ACADIA BLANCO
Code: ACD-BL-636
Size: 5.9x35.4"



ACADIA SPIGA BLANCO
Code: ACD-SP-BL
Size: 17.7x35.4"



ACADIA GRIS
Code: ACD-GR-636
Size: 5.9x35.4"



ACADIA SPIGA GRIS
Code: ACD-SP-GR
Size: 17.7x35.4"